

# SUPER SEAL B

## Water-Based Cure & Seal

### DESCRIPTION

**SUPER SEAL B** is a cross linking, styrene-acrylic copolymer solution formulated to achieve both a protective and decorative finish as well as allow the concrete to attain full mix design properties. **SUPER SEAL B** is a film-forming sealer, which will assist the curing of freshly placed concrete. **SUPER SEAL B** is formulated as follows:

**SUPER SEAL B-25** is a high solids water based curing and seal that meets ASTM C309 A and B and ASTM C1315

**SUPER SEAL B-15** is an economical low viscosity, low solids formula for easy sprayability that meets ASTM C309 A

### FEATURES

★ Satin Finish    ★ Low V.O.C.    ★ Sprayable    ★ Non-yellowing

### PREPARATION

Clean dirt, wax, grease, oil and other contaminants from the surface. Be sure to remove any foreign coating unless previous coating is same or similar water-based sealer. Make sure the surface is clean, dry and sound. Clean oily concrete with Clemons' DEGREASER NEUTRALIZER. Use a bristle brush for heavily oiled spots. If surface is slick, etch with Clemons' ETCH & CLEAN. Rinse well with Clemons' DEGREASER NEUTRALIZER and a pressure washer. Allow 24 hours to dry. Apply only when surface and air temperatures are above 50° F and below 90° F. Do not apply to excessively hot surfaces as rapid drying may cause bubbles or streaking to form.

### APPLICATION

Apply at substrate temperatures above 50° F. Apply with sprayer. If applying to fresh concrete, wait until all bleed water has evaporated. For exterior concrete, you may use a medium nap roller. For smooth concrete you may use a short nap roller and cross roll. Thoroughly saturate surface. Apply additional coats as needed. Foot traffic should be avoided for 4 hours. Vehicle traffic should be avoided for 48 hours. Cooler temperatures or increased humidity will slow the dry.

### NET COVERAGE RATE

Two thin coats are recommended.

Smooth Troweled: 300 ft<sup>2</sup> per gallon      Textured or Stamped: 200 ft<sup>2</sup> per gallon

Broom Swept: 200 ft<sup>2</sup> per gallon

### TECHNICAL DATA

### HMIS/NFPA

VOC: standard <180g/L

Health 1

Flammability 0

Flash Point: N/A

Reactivity 0

Protection B

Meets or Exceeds ASTM C-309, Type I Class A and B; ASTM C-1315 (WB-25 only); EPA 40 CFR Part D

### SLIP RESISTANCE

For additional slip resistance, apply one coat of SUPER SEAL WB. Mix SUPER GRIP into sealer and apply with second coat.

### CLEANUP

Clean up tools with water

### MAINTENANCE

Clean sealed surface with water only. Reseal surface every two years or as needed to prevent buildup of sealer.

**DISCLAIMER:** Since manufacturer has no control over handling, use or storage; no guarantee expressed or implied, is offered. The suitability of the product for use shall be solely up to the user. Manufacturer retains the right to venue.

Made in USA

**CLEMONS CONCRETE COATINGS**

505 Cave Road Nashville TN 37210 ★ www.ccc-usa.com ★ Tel: 615-872-9099 ★ Fax: 615-872-9052