



CLEMONS CONCRETE COATINGS

SUPER SEAL VX

SUPER SEAL VX is a high solids, low VOC, styrene-acrylic copolymer curing & sealing solution formulated to achieve both a protective and decorative finish as well as allow the concrete to attain full mix design properties. **SUPER SEAL VX** is a film forming sealer, which will assist the curing of freshly placed concrete. Two thin coats of **SUPER SEAL VX** are preferred to one thick coat.



- ★ **Slow Drying & Reduced Bubbling**
- ★ **Low Acetone Content**
- ★ **High Gloss**
- ★ **Wet Look**
- ★ **Cures & Seals Fresh Concrete**
- ★ **Available in High Solids – 25%**

 ***Our Most Affordable
Low VOC Formulation!***

Made in USA

CLEMONS CONCRETE COATINGS

505 Cave Road ★ Nashville TN 37210 ★ www.ccc-usa.com ★ Tel: 615-872-9099

SUPER SEAL VX

DESCRIPTION

SUPER SEAL VX is a Low VOC, styrene-acrylic copolymer solution formulated to achieve both a protective and decorative finish as well as allow the concrete to attain full mix design properties. **SUPER SEAL VX** is a film-forming sealer, which will assist the curing of freshly placed concrete. **SUPER SEAL VX** is formulated as follows:

SUPER SEAL-25 VX: Slow drying, High solids (25%) formulation for spray-ability. Two thin coats of **SUPER SEAL-25 VX** are preferred to one thick coat. Our most affordable Low VOC formulation.

BENEFITS

★ High Gloss ★ Wet Look ★ High Solids ★ U.V. Resistant ★ Economical ★ Less Problems

PREPARATION

Cured Concrete: Clean dirt, wax, grease, oil and other contaminants from the surface. Be sure to remove any foreign coating unless previous coating is same or similar solvent-based sealer. Make sure the surface is clean, dry and sound. Clean oily concrete with Clemons' **DEGREASER NEUTRALIZER**. Use a bristle brush for heavily oiled spots. If surface is slick, etch with Clemons' **ETCH & CLEAN**. Rinse well with Clemons' **DEGREASER NEUTRALIZER** and water preferably with a pressure washer. Allow 24 hours to dry. Apply only when surface and air temperatures are above 50° F and below 90° F. Do not apply to excessively hot surfaces as rapid drying may cause bubbles to form. For pavers, sweep away any loose sand.

APPLICATION

When applying to fresh concrete, wait until all bleed water has evaporated. For best results apply **SUPER SEAL VX** with a solvent-resistant sprayer. Hold conical spray tip no more than 8" from surface. If product must be rolled be sure to use a solvent-resistant non-shedding roller cover. Use a long nap roller for exposed aggregate, a medium nap roller for textured surfaces and a short nap roller for smooth surfaces. Keep roller soaked by dipping on every stroke. Every few feet turn perpendicular to the first coat, and cross roll without re-dipping. Wait until the surface is tack-free before applying a second coat. The continual dipping with the first coat gives a heavy application and the cross-rolling allows for an even application. Clean up immediately with aromatic solvent such as A-1 Solvent or Xylene. Do not thin product. Foot traffic should be avoided for 4 hours. Vehicle traffic should be avoided for 48 hours. Cooler temperatures or increased humidity will slow the dry.

NET COVERAGE RATE

Two thin coats are recommended with the following net coverage rates:

Smooth Troweled: 300 ft² per gallon

Uncured Broom Swept: 200 ft² per gallon

Textured or Stamped: 200 ft² per gallon

Exposed Aggregate and Pavers: 100 ft² per gallon

SLIP RESISTANCE

For additional slip resistance, apply one coat of **SUPER SEAL**. Mix **SUPER GRIP** into sealer and apply with second coat.

CLEANUP

Clean tools with A1 Solvent, Xylene or Lacquer Thinner immediately after use.

MAINTENANCE

Clean sealed surface with water only. Reseal surface no more than two years or as needed to prevent buildup of sealer.

TECHNICAL DATA

VOC: standard <350 g/L

Flash Point: 0°F

HMIS

Health	2	Flammability	3
Reactivity	0	Protection	B

SUPER SEAL-25 VX Meets or Exceeds: ASTM C-309, Type I Class A & B; ASTM C-1315; AASHTO Spec M-148; EPA 40 CFR Part D

DISCLAIMER: Since manufacturer has no control over handling, use or storage; no guarantee expressed or implied, is offered. The suitability of the product for use shall be solely up to the user. Manufacturer retains the right to venue.

Made in U.S.A.

CLEMONS CONCRETE COATINGS

505 Cave Rd ★ Nashville TN 37210 ★ www.ccc-usa.com ★ Tel: 615-872-9099 ★ Fax: 615-872-9052