

SUPER SEAL VT

Low VOC Solvent-Based Cure & Seal

DESCRIPTION

SUPER SEAL VT is a Low VOC, styrene-acrylic copolymer solution formulated to achieve both a protective and decorative finish as well as allow the concrete to attain full mix design properties. SUPER SEAL VT is a film-forming sealer, which will assist the curing of freshly placed concrete. SUPER SEAL VT is formulated as follows:

SUPER SEAL-25 VT: Available in Clear & Brown tinted. Slow drying, High solids (25%) formulation for spray-ability. Two coats of SUPER SEAL-25 VT are preferred to one thick coat. A better Low VOC formulation than the competition!

SUPER SEAL-19 VT: Available in Clear & Brown tinted. Slow drying, Lower Solids (19%) formulation for spray-ability. Great for resealing previously sealed surfaces. Two coats of SUPER SEAL-19 are preferred to one thick coat. A better Low VOC formulation than the competition!

FEATURES

★High Gloss ★Wet Look ★High Solids ★U.V. Resistant ★Slower Drying ★Easy to Spray

PREPARATION

Clean dirt, wax, grease, oil and other contaminants from the surface. Be sure to remove any foreign coating unless previous coating is same or similar solvent-based sealer. Make sure the surface is clean, dry and sound. Clean oily concrete with Clemons' CLEANER DEGREASER. Use a bristle brush for heavily oiled spots. If surface is slick, etch with Clemons' ETCH & CLEAN. Rinse well with a pressure washer. Allow 24 hours to dry. Apply only when surface and air temperatures are above 50° F and below 90° F. Do not apply to excessively hot surfaces as rapid drying may cause bubbles to form. For pavers, sweep away any loose sand.

APPLICATION

When applying to fresh concrete, wait until all bleed water has evaporated. For best results apply SUPER SEAL VT with a solvent-resistant sprayer. Hold conical spray tip no more than 8" from surface. If product must be rolled be sure to use a solvent-resistant non-shedding roller cover. Use a long nap roller for exposed aggregate, a medium nap roller for textured surfaces and a short nap roller for smooth surfaces. Keep roller soaked by dipping on every stroke. Every few feet turn perpendicular to the first coat, and cross roll without re-dipping. Wait until the surface is tack-free before applying a second coat. The continual dipping with the first coat gives a heavy application and the cross-rolling allows for an even application. Clean up immediately with aromatic solvent such as A-1 Solvent or Xylene. Do not thin product. Foot traffic should be avoided for 4 hours. Vehicle traffic should be avoided for 48-72 hours. Cooler temperatures or increased humidity will slow the dry.

NET COVERAGE RATE: Two thin coats are recommended.

Smooth Troweled:	300 ft ² per gallon	Textured or Stamped:	200 ft ² per gallon
Uncured Broom Swept:	200 ft ² per gallon	Exposed Aggregate and Pavers:	100 ft ² per gallon

TECHNICAL DATA

SUPER SEAL-25 VT VOC: <350 g/L
SUPER SEAL-19 VT VOC: <400 g/L
Flash Point: 40° F

HMIS

Health	2	Flammability	3
Reactivity	0	Protection	B

SUPER SEAL-25 VT Meets or Exceeds: ASTM C-309, Type I Class A & B; ASTM C-1315; AASHTO Spec M-148; EPA 40 CFR Part D

SUPER SEAL-19 VT Meets or Exceeds: ASTM C-309, Type I Class A & B. AASHTO Spec M-148; EPA 40 CFR Part D

SLIP RESISTANCE

For additional slip resistance, apply one coat of SUPER SEAL. Mix SUPER GRIP into sealer and apply with second coat.

CLEANUP

Clean tools with A1 Solvent or Xylene immediately after use.

MAINTENANCE

Clean sealed surface with water only. Reseal surface no more than two years or as needed to prevent buildup of sealer.

DISCLAIMER: Since manufacturer has no control over handling, use or storage; no guarantee expressed or implied, is offered. The suitability of the product for use shall be solely up to the user. Manufacturer retains the right to venue.

Made in USA

CLEMONS CONCRETE COATINGS

505 Cave Road Nashville TN 37210 ★ www.ccc-usa.com ★ Tel: 615-872-9099 ★ Fax: 615-872-9052