



CLEMONS CONCRETE COATINGS

SUPREME SEAL

Pure Acrylic Concrete Sealer



- ★ Solvent Based
- ★ Non-Yellowing
- ★ VOC compliant versions for all districts

- ★ High Gloss Wet Look
- ★ All types of concrete
- ★ Available in 1 gallon, 5 gallon, and 55 gallons

www.ccc-usa.com

SUPREME SEAL

Pure Acrylic Concrete Sealer

DESCRIPTION

SUPREME SEAL is a tough pure acrylic concrete sealer in a solvent base. It is designed to protect and beautify all types of concrete with a high gloss durable clear coating. Also available in MATTE finish. **SUPREME SEAL** is non-yellowing to preserve the appearance of all types of decorative concrete. **SUPREME SEAL** is formulated as follows:

FEDERAL <700 VOC Compliant: Available in 30% and 25%.
<600 VOC Compliant: Available in 19% solids.

LOW <400 VOC Compliant: **SUPREME VX** is a low acetone slow drying formula for easy application; available in 25% solids.
SUPREME VT is a no acetone slower drying formula for easier application; available in 25% and 19% solids.
SUPREME VZ is a no acetone and the slowest drying formula for the easiest application; available in 22% solids.

ULTRA LOW <100 VOC Compliant: **SUPREME VS** is a low acetone slow drying easy application formula; available in 23% solids.
SUPREME VC is special formulated to be compliant in all California Air Districts; available in 23% solids.

PREPARATION

Clean dirt, wax, grease, oil and other contaminants from the surface. Be sure to remove any foreign coating unless previous coating is same or similar solvent-based sealer. Make sure the surface is clean, dry and sound. Clean oily concrete with Clemons' **CLEANER DEGREASER NEUTRALIZER**. Use a bristle brush for heavily oiled spots. If surface is slick, etch with Clemons' **ETCH & CLEAN**. Rinse well with a pressure washer. Allow 24 hours to dry. Apply only when surface and air temperatures are above 50°F and below 90°F. Do not apply to excessively hot surfaces as rapid drying may cause bubbles to form. For pavers, sweep away any loose sand. **DO NOT THIN.**

APPLICATION

Brush may be used where roller won't reach. Do not pour directly from can to concrete. Apply evenly from can or other metal container with appropriate roller. Use a long nap roller for exposed aggregate, a medium nap roller for textured surfaces and a short nap roller for smooth surfaces. Wait until the surface is tack-free before applying a second coat. Apply perpendicular to the first coat. Cross-rolling allows for an even application. If spraying, use a solvent resistant sprayer holding tip no more than 8" from surface during application. Back rolling is recommended while spraying. Clean up immediately with A-1 Solvent, Xylene or Acetone. Foot traffic should be avoided for 4 hours. Vehicle traffic should be avoided for 48 hours. Cooler temperatures or increased humidity will slow the dry time.

NET COVERAGE RATE

Two thin coats are recommended with the following net coverage of:

Smooth Troweled: 300 ft² per gallon
Broom Swept: 200 ft² per gallon

Textured or Stamped: 200 ft² per gallon
Exposed Aggregate and Pavers: 100 ft² per gallon

SLIP RESISTANCE

For additional slip resistance, apply one coat of **SUPREME SEAL**. Mix Clemons' **SUPER GRIP** into sealer and apply with second coat.

CLEANUP

Clean tools with A1 Solvent, Acetone or Xylene.

MAINTENANCE

Clean sealed surface with water only. Reseal surface as needed but no more than every two years to prevent buildup of sealer.

TECHNICAL DATA

VOC compliant:

SUPREME 25 & 30: <700 g/L Flash point: 105°F
SUPREME 19: <600 g/L Flash point: 0°F
SUPREME VT & VZ: <400 g/L Flash point: 40°F
SUPREME VX: <400 g/L Flash point: 0°F
SUPREME VS: <100 g/L Flash point: 40°F
SUPREME VC: <100 g/L Flash point: 0°F

HMIS

SUPREME 30 & 25:

Health	2	Flammability	2
Reactivity	0	Protection	B

SUPREME 19, VX, VT, VZ, VS and VC:

Health	2	Flammability	3
Reactivity	0	Protection	B

DISCLAIMER: Since manufacturer has no control over handling, use or storage; no guarantee expressed or implied, is offered. The suitability of the product for use shall be solely up to the user. Manufacturer retains the right to venue.

Made in U.S.A.

CLEMONS CONCRETE COATINGS

505 Cave Rd ★ Nashville TN 37210 ★ www.ccc-usa.com ★ Tel: 615-872-9099 ★ Fax: 615-872-9052