



# CLEMONS CONCRETE COATINGS

## SUPER SEAL 30 EXPOSED AGGREGATE SEALER



**SUPER SEAL 30** is a 30% solids styrene-acrylic copolymer sealer for exposed aggregate. Available in **CLEAR** for all types of aggregate and decorative concrete, **BROWN** tint for exposed pea gravel aggregate, and **GRAY** tint for exposed chipped limestone. **SUPER SEAL 30** will enhance and protect the surface of the concrete. **SUPER SEAL 30** can be used as a cure and seal for fresh concrete.

- ★ Clear, Brown, & Gray Tinted
- ★ High-Gloss
- ★ Wet-Look
- ★ Solvent-Based
- ★ 30% Solids
- ★ Seals & Protects
- ★ Decorative Finish
- ★ Cure & Seal



**CLEAR**



**BROWN**



**GRAY**



For more information: [www.clemonsconcretecoatings.com](http://www.clemonsconcretecoatings.com)

# SUPER SEAL-30

## DESCRIPTION

**SUPER SEAL 30** is a premium solvent-based concrete sealer specifically formulated for exposed aggregate concrete. This high solids, styrene-acrylic copolymer solution is formulated to achieve both a protective and decorative finish. Along with protecting concrete surfaces against water seepage and aggregate loosening due to freeze/thaw conditions, **SUPER SEAL 30** beautifies the surface with a high-gloss finish that shines and darkens as it protects.

## USES

Seals, protects, and adds gloss to exposed aggregate concrete.

★ **CLEAR** for use on all types of exposed aggregate concrete and concrete pavers.

★ **BROWN TINT** for use on exposed pea gravel concrete.

★ **GRAY TINT** for use on exposed gray chipped limestone concrete.

## ALTERNATIVE USES

**SUPER SEAL 30** can also be used as a cure and seal for aiding the curing of fresh concrete and a decorative sealer for other types of existing concrete and concrete pavers. See data sheet for more info.

## PREPARATION

Clean dirt, wax, grease, oil and other contaminants from the surface. Be sure to remove any foreign coating unless previous coating is same or similar solvent-based sealer. Make sure the surface is clean, dry and sound. Clean oily concrete with our **CLEANER DEGREASER NEUTRALIZER**. Use a bristle brush for heavily oiled spots. Rinse well with a pressure washer. Allow 24 hours to dry. Apply only when surface and air temperatures are above 50° F and below 90° F. Do not apply to excessively hot surfaces or surfaces that are experiencing large changes in temperature as this may cause bubbles to form.

If surface is slick, etch with our **ETCH & CLEAN**. For pavers, sweep away any loose sand.

**Not for use on cured, broom-finished concrete.**

## APPLICATION

Apply evenly from can or other metal container with appropriate roller. Use a long nap roller for exposed aggregate. Keep roller soaked by dipping on every stroke. Every few feet turn perpendicular to the first coat, and cross roll without re-dipping. Wait until the surface is tack-free before applying a second coat. The continual dipping with the first coat gives a heavy application and the cross-rolling allows for an even application. Clean up immediately with aromatic solvent such as **A-1 SOLVENT** or Xylene. Do not thin product. Foot traffic should be avoided for 4 hours. Vehicle traffic should be avoided for 48 hours. Cooler temperatures or increased humidity will slow the cure time. Do not pour directly from can directly onto concrete. If applying to fresh concrete, apply after all bleed water has evaporated and all finish work has been completed.

## NET COVERAGE RATE

Two thin coats are recommended. One coat application is possible if applied at proper rate and cross-rolled.

Exposed Aggregate and Pavers:	100 ft <sup>2</sup> per gallon	Textured or Stamped:	200 ft <sup>2</sup> per gallon
Smooth Troweled:	300 ft <sup>2</sup> per gallon	Fresh Broomed Concrete:	200 ft <sup>2</sup> per gallon

## TECHNICAL DATA

VOC: standard <700 g/L

Flash Point: 106° F

## HMIS

Health	2	Flammability	3
Reactivity	0	Protection	B

Meets or Exceeds: ASTM C-309, Type I Class A and B; ASTM C-1315-11; AASHTO Spec M-148; EPA 40 CFR Part D

## CLEANUP

Clean up tools with **A1-SOLVENT** or Xylene.

## MAINTENANCE

Clean sealed surface with water only. Reseal surface every two years or as needed to prevent buildup of sealer.

**DISCLAIMER:** Since the manufacturer has no control over handling, use, or storage; no guarantee expressed or implied, is offered. The suitability of the product for use shall be solely up to the user. The manufacturer retains the right to the venue

Made in USA

**CLEMONS CONCRETE COATINGS**

505 Cave Road Nashville TN 37210 ★ [www.ccc-usa.com](http://www.ccc-usa.com) ★ Tel: 615-872-9099 ★ Fax: 615-872-9052

2023