

SUPER SEAL VX

Low VOC Solvent-Based Cure & Seal

DESCRIPTION

SUPER SEAL VX is a Low VOC, styrene-acrylic copolymer solution formulated to achieve both a protective and decorative finish as well as allow the concrete to attain full mix design properties. SUPER SEAL VX is a film-forming sealer, which will assist the curing of freshly placed concrete. SUPER SEAL VX is formulated as follows:

SUPER SEAL-25 VX: Slow drying, High solids (25%) formulation for spray-ability. Two thin coats of SUPER SEAL-25 VX are preferred to one thick coat. Our Best Low VOC formulation.

SUPER SEAL-19 VX: Mid-solids (19%) formulation for spray-ability. Two thin coats of SUPER SEAL-19 VX are preferred to one thick coat. Our most affordable Low VOC formulation.

FEATURES

★High Gloss ★Wet Look ★High Solids ★U.V. Resistant ★Economical

PREPARATION

Cured Concrete: Clean dirt, wax, grease, oil and other contaminants from the surface. Be sure to remove any foreign coating unless previous coating is same or similar solvent-based sealer. Make sure the surface is clean, dry and sound. Clean oily concrete with Clemons' CLEANER DEGREASER. Use a bristle brush for heavily oiled spots. If surface is slick, etch with Clemons' ETCH & CLEAN. Rinse well with a pressure washer. Allow 24 hours to dry. Apply only when surface and air temperatures are above 50° F and below 90° F. Do not apply to excessively hot surfaces as rapid drying may cause bubbles to form. For pavers, sweep away any loose sand.

APPLICATION

If applying to fresh concrete, wait until all bleed water has evaporated. For best results SUPER SEAL VX should be sprayed using a solvent resistant sprayer. Hold spray tip no more than 8 inches from surface. Do not thin product. Foot traffic should be avoided for 4 hours. Vehicle traffic should be avoided for 48-72 hours. Cooler temperatures or increased humidity will slow the dry.

NET COVERAGE RATE: Two thin coats are recommended.

Smooth Troweled:	300 ft ² per gallon	Textured or Stamped:	200 ft ² per gallon
Uncured Broom Swept:	200 ft ² per gallon	Exposed Aggregate and Pavers:	100 ft ² per gallon

TECHNICAL DATA

VOC: standard <350 g/L
Flash Point: 0° F
DOT: UN1263, Paint 3, PG II

HMIS

Health	2	Flammability	3
Reactivity	0	Protection	B

SUPER SEAL-25 VX Meets or Exceeds: ASTM C-309, Type I Class A & B; ASTM C-1315; AASHTO Spec M-148; EPA 40 CFR Part D
SUPER SEAL-19 VX Meets or Exceeds: ASTM C-309, Type I Class A & B. AASHTO Spec M-148; EPA 40 CFR Part D

SLIP RESISTANCE

For additional slip resistance, apply one coat of SUPER SEAL. Mix SUPER GRIP into sealer and apply with second coat.

CLEANUP

Clean tools with A1 Solvent or Xylene immediately after use.

MAINTENANCE

Clean sealed surface with water only. Reseal surface no more than two years or as needed to prevent buildup of sealer.

DISCLAIMER: Since manufacturer has no control over handling, use or storage; no guarantee expressed or implied, is offered. The suitability of the product for use shall be solely up to the user. Manufacturer retains the right to venue.

Made in USA

CLEMONS CONCRETE COATINGS

505 Cave Road Nashville TN 37210 ★ www.ccc-usa.com ★ Tel: 615-872-9099 ★ Fax: 615-872-9052